

## Adhesive to film supported foam (Current)

Product Information	Description
Adhesive	Rubber
Release Liner	Silicone coated paper
Application Temperature (°F)	65 to 100
Service Temperature (°F)	-20 to 150

Adhesive*	Typical Value	Test Method
Shear Adhesion (minutes): 1in <sup>2</sup> , 10lb, 72°F	250.0	PSTC-107
Shear Adhesion (minutes): 1in <sup>2</sup> , 2kg, 72°F	5000.0	PSTC-107
Shear Adhesion (minutes): 1in <sup>2</sup> , 500g, 150°F	10.0	PSTC-107
180° Peel Adhesion SS (lb/in)	8.0	PSTC-101
90° Peel Adhesion SS (lb/in)	4.8	PSTC-101
90° Peel Adhesion Rigid PVC (lb/in)	4.2	PSTC-101
90° Peel Adhesion PP (lb/in)	4.0	PSTC-101
Quick Stick SS (lb/in):	3.9	PSTC-5
Quick Stick PP (lb/in):	1.0	PSTC-5
Loop Tack SS (lb/in):	8.7	PSTC-16
Loop Tack Rigid PVC (lb/in):	6.1	PSTC-16
Loop Tack PP (lb/in):	6.7	PSTC-16

\*Tests are performed on 2 mil PET

### Storage

Tape should be stored within its' original packaging, in a dry place at Room Temperature (72°F). If room temperature is not possible, the storage temperatures should not exceed 39°F to 100°F. When the tape is stored under these conditions, the shelf life would be 18 months from the date of shipment.

Duraco provides this information and recommendations for informative purposes only. The data is intended as a guide only and is presented without guarantees and without assumption of liabilities resultant from the use of information provided.

[duraco.com](http://duraco.com)

7400 Industrial Drive, Forest Park, IL 60130 | Phone: (866) 800-0775 | [sales@duraco.com](mailto:sales@duraco.com)