

Tear Tape 60

Material Description: 60 micron thick Tear Tape is designed to be an opening device for board- and paper-based packaging. Intuitive to use and easy to implement, it gives fast, safe, and immediate access to the contents of corrugated and fiberboard packaging.



Property	Units	Typical Value	Test Method
Carrier		MOPP	
Film Thickness	μm	60 ± 3	AFERA 5006
Total Tape Thickness	μm	87 ± 10	AFERA 5006
Breaking Strength	Kgf/25mm	≥ 52	AFERA 5004
Elongation at Break	%	≥ 20	AFERA 5004
Tensile Strength at Break	Kgf/mm ²	≥ 34	AFERA 5004
Peel Adhesion to Stainless Steel	gf/25mm	≥ 800	FINAT FTM 1
Loop Tack to Glass	gf/25mm	≥ 800	FINAT FTM 0

Storage

Tape should be stored within its' original packaging, in a dry place at Room Temperature (72°F). If room temperature is not possible, the storage temperatures should not exceed 39°F to 100°F. When the tape is stored under these conditions, the shelf life would be 18 months from the date of shipment.

Duraco provides this information and recommendations for informative purposes only. The data is intended as a guide only and is presented without guarantees and without assumption of liabilities resultant from the use of information provided.

duraco.com

7400 Industrial Drive, Forest Park, IL 60130 | Phone: (866) 800-0775 | sales@duraco.com