## **Product Specification Sheet**



## **DURACO® HIGH BOND 14**

**Material Description:** Duraco® High Bond 14 utilizes multi purpose acrylic adhesive on both sides of firm foam. The adhesive provides excellent adhesion to a wide range of high and medium surface energy substrates including metal, glass and different types of plastics. The foam core provides good contact to applied surface. Replaces rivets, welds, and mechanical fasteners. Duraco® High Bond 14 is ideal for interior and exterior use with its good resistance to temperature cycles and moisture.



**ASTM D3654** 

| Product Information                               | Description             |             |
|---|-------------------------|-------------|
| Product Color                                     | Gray                    |             |
| Adhesive  | General Purpose Acrylic |             |
| Carrier   | Acrylic Foam            |             |
| Application Temperature (°F)                      | 70 to 100               |             |
| Service Temperature (°F)                          | -20 to 200              |             |
| Thickness (inch)                                  | 0.045                   |             |
|   |                         |             |
| DHB   | Typical Properties      | Test Method |
| 90° Peel Adhesion (lb/in):                        | 24                      | ASTM D3330  |
| Normal Tensile - T-Block (lb/0.5in <sup>2</sup> ) | 114                     | ASTM D897   |
| Dynamic Shear (lb/0.5in²):                        | 145                     | ASTM D1002  |
| Static Shear (minutes)                            |                         |             |
| 1.0 in <sup>2</sup> , 72°F, 10lb load             | 2,200                   | ASTM D3654  |
| Static Shear (minutes)                            |                         |             |

<sup>\*</sup>Tests are performed on 2 mil PET

1.0 in<sup>2</sup>, 150°F, 500 gram load

## **Storage**

Tape should be stored within its' original packaging, in a dry place at Room Temperature (72°F). If room temperature is not possible, the storage temperatures should not exceed 39°F to 100°F. When the tape is stored under these conditions, the shelf life would be 18 months from the date of shipment.

10,000

Duraco provides this information and recommendations for informative purposes only. The data is intended as a guide only and is presented without guarantees and without assumption of liabilities resultant from the use of information provided.